

Controllable deformations of unconstrained ideal nematic elastomers

L. Angela Mihai^{*} Alain Goriely[†]

September 30, 2023

Abstract

We establish that, for ideal unconstrained uniaxial nematic elastomers described by a homogeneous isotropic strain-energy density function, the only smooth deformations that can be controlled by the application of surface tractions only and are universal in the sense that they are independent of the strain-energy density are those for which the deformation gradient is constant and the liquid crystal director is either aligned uniformly or oriented randomly in Cartesian coordinates. This result generalizes the classical Ericksen’s theorem for nonlinear homogeneous isotropic hyperelastic materials. While Ericksen’s theorem is directly applicable to liquid crystal elastomers in an isotropic phase where the director is oriented randomly, in a nematic phase, the constitutive strain-energy density must account also for the liquid crystal orientation which leads to significant differences in the analysis compared to the purely elastic counterpart.

Key words: nematic elastomers, objectivity, isotropy, controllable deformations, director orientation, surface traction

1 Introduction

Liquid crystal elastomers (LCEs) are advanced multifunctional materials that combine elasticity with orientational order [32]. Specifically, mechanical strains give rise to changes in liquid crystalline order and, conversely, changes in the orientational order generate mechanical stresses and strains. Because of their large reversible deformations and complex material responses in the presence of external stimuli, such as heat, light, electric or magnetic fields, LCEs are suitable for a wide range of applications in science, manufacturing, and medical research [4].

LCEs can be synthesized by various methods. Without special aligning mechanisms, poly-domain samples are typically obtained where the material contains multiple subdomains, each of them with their own nematic alignment, termed the “director”. Monodomain LCEs can be achieved by a secondary cross-linking after electric or magnetic fields are applied or the material is mechanically deformed to induce the desired nematic orientation.

Sitting between the world of elastomers and that of liquid crystals, the analysis of LCEs can take advantage of developments in both these fields [22]. For unconstrained isotropic hyperelastic materials, it is well known that the only *controllable* deformations that can be maintained *universally*, i.e., independently of the material parameters, by application of surface tractions only, are those characterized by a constant deformation gradient in Cartesian coordinates, the so-called *homogeneous deformations*. This fundamental result due to Ericksen (1955) [8] (see also [29] for an alternative proof) has been central to the phenomenological study of many elastic materials for which constitutive parameters are derived from macroscopic experimental tests.

^{*}Corresponding author: L.A. Mihai, School of Mathematics, Cardiff University, Cardiff, UK, email: MihaiLA@cardiff.ac.uk.

[†]Mathematical Institute, University of Oxford, UK.

The problem of controllable deformations for incompressible homogeneous isotropic hyperelastic materials is much more involved and was examined in [7,17,21]. We refer also to [28] for a review of these results. Extensions of the analysis to anisotropic elasticity are presented in [34,35] and to anelasticity in [14,33].

In addition, nematic elastomers can sustain large reversible deformations under small applied forces [10,15,16,18,19,26,27,31,36]. For ideal LCEs, the theoretical explanation is that the energy depending isotropically on the macroscopic deformation only through the relative strain of the microstructure is minimized by these materials through a *force-free state*, resulting in the so-called *soft-elasticity* phenomenon, where the microstructure consists of many homogeneously deformed parts, known as *shear striping* [1,2,5,6]. Strain-energy densities depending also on the macroscopic strain to realistically account for *semi-soft elasticity* where the applied force required is small were proposed in [11–13] (see also [23,24]).

In this paper, we consider ideal unconstrained uniaxial nematic LCEs characterized by a homogeneous isotropic hyperelastic strain-energy density and subject to surface tractions only, i.e., in the absence of body forces. We prove that, in Cartesian coordinates, assuming that the deformation gradient is sufficiently smooth, the deformation is always homogeneous, i.e., it has a constant deformation gradient, while the liquid crystal director is either uniformly aligned or oriented randomly. If we weaken the smoothness assumption, then multiple solutions with locally constant deformation gradients can exist, such as the classical shear striping. This result is a direct extension of Ericksen’s theorem for compressible elastic materials [8] to ideal LCEs. The case where LCEs are modelled as incompressible materials [1,20,24] is also of considerable interest, but will not be discussed here.

2 Ideal liquid crystal elastomers

An ideal uniaxial nematic LCE can be described by a homogeneous strain-energy density function of the form [22]

$$W^{(nc)}(\mathbf{F}, \mathbf{n}) = W(\mathbf{A}), \quad (1)$$

where \mathbf{F} represents the macroscopic deformation gradient from the cross-linking state, \mathbf{n} is the nematic director (a unit vector for the localized direction of uniaxial nematic alignment) in the present configuration, and $W(\mathbf{A})$ is the strain-energy density of the isotropic polymer network, depending only on the (local) elastic deformation tensor \mathbf{A} . The tensors \mathbf{F} and \mathbf{A} satisfy the following relation [32],

$$\mathbf{F} = \mathbf{G}\mathbf{A}\mathbf{G}_0^{-1}, \quad (2)$$

where

$$\mathbf{G} = \left(a^{1/3} - a^{-\nu/3} \right) \mathbf{n} \otimes \mathbf{n} + a^{-\nu/3} \mathbf{I} \quad (3)$$

is the nematicity-induced (natural) deformation tensor defining a change of frame of reference from the isotropic to a nematic phase. In equation (3), $a > 0$ is a light- or temperature-dependent shape parameter, ν represents the optothermal analogue to the Poisson ratio relating responses in directions parallel or perpendicular to the director \mathbf{n} , \otimes denotes the tensor product of two vectors, and $\mathbf{I} = \text{diag}(1, 1, 1)$ is the identity tensor, with $\text{diag}(\cdot, \cdot, \cdot)$ denoting the diagonal second order tensor. We assume both a and ν to be spatially independent. The tensor \mathbf{G}_0 has a similar expression to that of \mathbf{G} , with \mathbf{n}_0 instead of \mathbf{n} , a_0 instead of a , and ν_0 instead of ν , corresponding to the reference cross-linking state. The director \mathbf{n} is an observable (spatial) quantity, and may differ from \mathbf{n}_0 by a rotation.

The square of the natural deformation tensor, known as the *step-length tensor*, takes the equivalent form [9] (see also [25]),

$$\mathbf{G}^2 = c(\mathbf{I} + 2\mathbf{Q}), \quad (4)$$

where c is the effective step length of the polymeric chain and \mathbf{Q} is the symmetric traceless order parameter tensor describing orientational order in nematic liquid crystals [32, Chapter 3]. In an isotropic phase, where the liquid crystal molecules are randomly oriented, $\mathbf{Q} = \mathbf{0}$ [32, Section 2.2].

In practice, LCEs can be modeled as incompressible materials at the cost of imposing an extra constraint, namely $\det \mathbf{F} = 1$. However, here we consider universal solutions for unconstrained LCEs, i.e., incompressibility is not enforced.

In equation (1), the elastic strain-energy density W is minimized by any deformation satisfying $\mathbf{A}\mathbf{A}^T = \mathbf{I}$, and the nematic strain-energy function $W^{(nc)}$ is minimized by any deformation satisfying $(\mathbf{F}\mathbf{G}_0)(\mathbf{F}\mathbf{G}_0)^T = \mathbf{G}^2$. Without loss of generality, we assume that the strain-energy density described by equation (1) vanishes in the reference state where $\mathbf{F} = \mathbf{I}$ and $\mathbf{G} = \mathbf{G}_0$.

By (3), if \mathbf{R} is a rigid-body rotation, then the following identity holds

$$\mathbf{R}^T \mathbf{G} \mathbf{R} = \left(a^{1/3} - a^{-\nu/3} \right) \left(\mathbf{R}^T \mathbf{n} \right) \otimes \left(\mathbf{R}^T \mathbf{n} \right) + a^{-\nu/3} \mathbf{I}. \quad (5)$$

Since nematic elastomers are weakly cross-linked, the nematic director can rotate freely, and the material displays isotropic mechanical properties. Then, the strain-energy density given by (1) satisfies the following conditions inherited from isotropic finite elasticity [22]:

(C1) Objectivity/Frame-indifference. The constitutive equation is unaffected by a superimposed rigid-body transformation (which involves a change of position after deformation). As \mathbf{n} is defined with respect to the deformed configuration, it transforms when this configuration is rotated, whereas \mathbf{n}_0 does not. Material objectivity is guaranteed by defining strain-energy functions in terms of the scalar invariants.

This is because, by the material frame indifference of W ,

$$W(\mathbf{R}^T \mathbf{A}) = W(\mathbf{A}), \quad (6)$$

and by (2),

$$\mathbf{R}^T \mathbf{F} = \left(\mathbf{R}^T \mathbf{G} \mathbf{R} \right) \left(\mathbf{R}^T \mathbf{A} \right) \mathbf{G}_0^{-1}. \quad (7)$$

Then (1), (5), (6) and (7) imply

$$W^{(nc)}(\mathbf{R}^T \mathbf{F}, \mathbf{R}^T \mathbf{n}) = W(\mathbf{R}^T \mathbf{A}) = W(\mathbf{A}) = W^{(nc)}(\mathbf{F}, \mathbf{n}). \quad (8)$$

(C2) Isotropy. The constitutive equation is unaffected by a rigid-body transformation prior to deformation. As \mathbf{n} is defined with respect to the deformed configuration, it does not change when the reference configuration is rotated, whereas \mathbf{n}_0 does. For isotropic materials, the strain-energy function is a symmetric function of the principal stretch ratios.

This is because, since W is isotropic, i.e.,

$$W(\mathbf{A}) = W(\mathbf{A}\mathbf{R}), \quad (9)$$

and (2) holds, it follows that

$$\mathbf{F}\mathbf{R} = \mathbf{G}(\mathbf{A}\mathbf{R}) \left(\mathbf{R}^T \mathbf{G}_0^{-1} \mathbf{R} \right). \quad (10)$$

Then, by (1), (9) and (10),

$$W^{(nc)}(\mathbf{F}\mathbf{R}, \mathbf{n}) = W(\mathbf{A}\mathbf{R}) = W(\mathbf{A}) = W^{(nc)}(\mathbf{F}, \mathbf{n}). \quad (11)$$

Under the frame-indifference condition (C1), the LCE model defined by (1) can be expressed equivalently in terms of the scalar invariants [30], as follows:

$$W^{(nc)} \left(I_1^{(nc)}, I_2^{(nc)}, I_3^{(nc)}, I_4^{(nc)}, I_5^{(nc)} \right) = W(I_1, I_2, I_3), \quad (12)$$

where

$$I_1^{(nc)} = \text{tr} \left(\mathbf{F} \mathbf{G}_0^2 \mathbf{F}^\top \right) = \text{tr} \left(\mathbf{F}^\top \mathbf{G}_0^2 \mathbf{F} \right), \quad (13)$$

$$I_2^{(nc)} = \text{tr} \left[\text{Cof} \left(\mathbf{F} \mathbf{G}_0^2 \mathbf{F}^\top \right) \right] = \text{tr} \left[\text{Cof} \left(\mathbf{F}^\top \mathbf{G}_0^2 \mathbf{F} \right) \right], \quad (14)$$

$$I_3^{(nc)} = \det \left(\mathbf{F} \mathbf{G}_0^2 \mathbf{F}^\top \right) = \det \left(\mathbf{F}^\top \mathbf{G}_0^2 \mathbf{F} \right), \quad (15)$$

$$I_4^{(nc)} = \mathbf{n} \cdot \mathbf{F} \mathbf{G}_0^2 \mathbf{F}^\top \mathbf{n}, \quad (16)$$

$$I_5^{(nc)} = \mathbf{n} \cdot \left(\mathbf{F} \mathbf{G}_0^2 \mathbf{F}^\top \right)^2 \mathbf{n}, \quad (17)$$

and $\{I_1, I_2, I_3\}$ are the principal invariants of the elastic Cauchy-Green tensors $\mathbf{A} \mathbf{A}^\top$ and $\mathbf{A}^\top \mathbf{A}$.

The following relations between $\{I_1^{(nc)}, I_2^{(nc)}, I_3^{(nc)}, I_4^{(nc)}, I_5^{(nc)}\}$ and $\{I_1, I_2, I_3\}$ are obtained:

$$I_3 = (\det \mathbf{A})^2 = [\det \mathbf{G}^{-1} \det (\mathbf{F} \mathbf{G}_0)]^2 = a^{2(2\nu-1)/3} I_3^{(nc)}, \quad (18)$$

where $\det \mathbf{G} = a^{(1-2\nu)/3}$,

$$\begin{aligned} I_1 &= \text{tr} \left(\mathbf{A}^\top \mathbf{A} \right) \\ &= \text{tr} \left[(\mathbf{F} \mathbf{G}_0)^\top \mathbf{G}^{-2} (\mathbf{F} \mathbf{G}_0) \right] \\ &= a^{2\nu/3} \left[\text{tr} \left(\mathbf{F} \mathbf{G}_0^2 \mathbf{F}^\top \right) - \left(1 - a^{-2(\nu+1)/3} \right) \mathbf{n} \cdot \left(\mathbf{F} \mathbf{G}_0^2 \mathbf{F}^\top \right) \mathbf{n} \right] \\ &= a^{2\nu/3} \left[I_1^{(nc)} - \left(1 - a^{-2(\nu+1)/3} \right) I_4^{(nc)} \right], \end{aligned} \quad (19)$$

and, using (18),

$$\begin{aligned} I_2 &= I_3 \text{tr} \left(\mathbf{A}^\top \mathbf{A} \right)^{-\top} \\ &= a^{2(2\nu-1)/3} I_3^{(nc)} \text{tr} \left[(\mathbf{F} \mathbf{G}_0)^{-1} \mathbf{G}^2 (\mathbf{F} \mathbf{G}_0)^{-\top} \right] \\ &= a^{2(2\nu-1)/3} I_3^{(nc)} a^{-2\nu/3} \left[\text{tr} \left(\mathbf{F}^{-\top} \mathbf{G}_0^{-2} \mathbf{F}^{-1} \right) - \left(1 - a^{2(\nu+1)/3} \right) \mathbf{n} \cdot \left(\mathbf{F}^{-\top} \mathbf{G}_0^{-2} \mathbf{F}^{-1} \right) \mathbf{n} \right] \\ &= a^{2(\nu-1)/3} \left[I_2^{(nc)} - \left(1 - a^{2(\nu+1)/3} \right) \left(I_5^{(nc)} - I_1^{(nc)} I_4^{(nc)} + I_2^{(nc)} \right) \right]. \end{aligned} \quad (20)$$

Note that the above expression for I_2 holds since, by the Cayley-Hamilton theorem, we have

$$\left(\mathbf{F} \mathbf{G}_0 \mathbf{F}^\top \right)^3 - I_1^{(nc)} \left(\mathbf{F} \mathbf{G}_0 \mathbf{F}^\top \right)^2 + I_2^{(nc)} \left(\mathbf{F} \mathbf{G}_0 \mathbf{F}^\top \right) - I_3^{(nc)} \mathbf{I} = 0, \quad (21)$$

and multiplying the above equation by $(\mathbf{F} \mathbf{G}_0^2 \mathbf{F}^\top)^{-1}$ gives

$$I_3^{(nc)} \left(\mathbf{F} \mathbf{G}_0^2 \mathbf{F}^\top \right)^{-1} = \left(\mathbf{F} \mathbf{G}_0^2 \mathbf{F}^\top \right)^2 - I_1^{(nc)} \left(\mathbf{F} \mathbf{G}_0^2 \mathbf{F}^\top \right) + I_2^{(nc)} \mathbf{I}. \quad (22)$$

Hence,

$$\begin{aligned} \mathbf{n} \cdot \mathbf{F}^{-\top} \mathbf{G}_0^{-2} \mathbf{F}^{-1} \mathbf{n} &= \mathbf{n} \cdot \left(I_3^{(nc)} \right)^{-1} \left[\left(\mathbf{F} \mathbf{G}_0^2 \mathbf{F}^\top \right)^2 - I_1^{(nc)} \left(\mathbf{F} \mathbf{G}_0^2 \mathbf{F}^\top \right) + I_2^{(nc)} \mathbf{I} \right] \mathbf{n} \\ &= \left(I_3^{(nc)} \right)^{-1} \left(I_5^{(nc)} - I_1^{(nc)} I_4^{(nc)} + I_2^{(nc)} \right). \end{aligned} \quad (23)$$

By the isotropy condition (C2), the LCE model given by (1) can be written equivalently as

$$W^{(nc)}(\lambda_1, \lambda_2, \lambda_3, \mathbf{n}) = W(\alpha_1, \alpha_2, \alpha_3), \quad (24)$$

where $\lambda_1^2, \lambda_2^2, \lambda_3^2$ are the principal eigenvalues of $\mathbf{F}\mathbf{G}_0^2\mathbf{F}^T$ and $\alpha_1^2, \alpha_2^2, \alpha_3^2$ are the principal eigenvalues of $\mathbf{A}^T\mathbf{A}$. The following relations between these principal eigenvalues and the corresponding principal invariants hold,

$$I_1^{(nc)} = \lambda_1^2 + \lambda_2^2 + \lambda_3^2, \quad I_2^{(nc)} = \lambda_1^2\lambda_2^2 + \lambda_2^2\lambda_3^2 + \lambda_3^2\lambda_1^2, \quad I_3^{(nc)} = \lambda_1^2\lambda_2^2\lambda_3^2, \quad (25)$$

and

$$I_1 = \alpha_1^2 + \alpha_2^2 + \alpha_3^2, \quad I_2 = \alpha_1^2\alpha_2^2 + \alpha_2^2\alpha_3^2 + \alpha_3^2\alpha_1^2, \quad I_3 = \alpha_1^2\alpha_2^2\alpha_3^2, \quad (26)$$

as usual.

3 Stresses and stress-free configurations

For nematic LCEs, the director is ‘free’ to rotate, hence \mathbf{F} and \mathbf{n} are independent variables. Since \mathbf{G} and \mathbf{G}_0 are symmetric, the Cauchy stress tensor for the nematic material with the strain-energy function described by (1) is calculated as follows [22],

$$\begin{aligned} \mathbf{T}^{(nc)} &= J^{-1} \frac{\partial W^{(nc)}}{\partial \mathbf{F}} \mathbf{F}^T \\ &= J^{-1} \mathbf{G}^{-1} \frac{\partial W}{\partial \mathbf{A}} \mathbf{A}^T \mathbf{G} \\ &= (\det \mathbf{G}^{-1} \det \mathbf{G}_0) \mathbf{G}^{-1} \mathbf{T} \mathbf{G}, \end{aligned} \quad (27)$$

where $J = \det \mathbf{F} = \det \mathbf{G} \det \mathbf{A} \det \mathbf{G}_0^{-1}$ and

$$\mathbf{T} = (\det \mathbf{A})^{-1} \frac{\partial W}{\partial \mathbf{A}} \mathbf{A}^T \quad (28)$$

is the Cauchy stress tensor from isotropic finite elasticity. Equivalently,

$$\mathbf{T} = \beta_0 \mathbf{I} + \beta_1 \mathbf{B} + \beta_{-1} \mathbf{B}^{-1}, \quad (29)$$

where

$$\beta_0 = \frac{2}{\sqrt{I_3}} \left(I_2 \frac{\partial W}{\partial I_2} + I_3 \frac{\partial W}{\partial I_3} \right), \quad \beta_1 = \frac{2}{\sqrt{I_3}} \frac{\partial W}{\partial I_1}, \quad \beta_{-1} = -2\sqrt{I_3} \frac{\partial W}{\partial I_2} \quad (30)$$

are scalar functions of the principal invariants $\{I_1, I_2, I_3\}$ of $\mathbf{B} = \mathbf{A}\mathbf{A}^T$.

The first Piola-Kirchhoff stress tensor for the nematic material is equal to

$$\mathbf{P}^{(nc)} = \mathbf{T}^{(nc)} \text{Cof } \mathbf{F} = \frac{\partial W^{(nc)}}{\partial \mathbf{F}} = \mathbf{G}^{-1} \frac{\partial W}{\partial \mathbf{A}} = \mathbf{G}^{-1} \mathbf{P}, \quad (31)$$

where $\text{Cof } \mathbf{F} = J\mathbf{F}^{-T}$ and

$$\mathbf{P} = \frac{\partial W}{\partial \mathbf{A}} \quad (32)$$

is the first Piola-Kirchhoff stress tensor from isotropic elasticity.

The corresponding second Piola-Kirchhoff stress tensor is

$$\mathbf{S}^{(nc)} = \mathbf{F}^{-1} \mathbf{P}^{(nc)} = \mathbf{G}_0 \mathbf{A}^{-1} \mathbf{G}^{-2} \mathbf{P} \mathbf{G}_0 = \mathbf{G}_0 \mathbf{A}^{-1} \mathbf{G}^{-2} \mathbf{A} \mathbf{S} \mathbf{G}_0, \quad (33)$$

where $\mathbf{S} = \mathbf{A}^{-1} \mathbf{P}$ is the second Piola-Kirchhoff from isotropic elasticity.

Since the relation (29) between the Cauchy stress tensor \mathbf{T} and the Cauchy-Green tensor \mathbf{B} is not invertible in general, more than one deformation gradient \mathbf{A} may induce the same stress tensor \mathbf{T} . Thus the Cauchy stress tensor $\mathbf{T}^{(nc)}$ in a nematic LCE may also be generated by more than one deformation gradient \mathbf{F} . Such deformations corresponding to the same stress tensor can also alternate in LCE materials to produce inhomogeneous patterns. In this case, for geometric compatibility, any two different gradient tensors \mathbf{F} and $\hat{\mathbf{F}}$ corresponding to two alternating phases must be rank-one connected, i.e., $\text{rank}(\mathbf{F} - \hat{\mathbf{F}}) = 1$.

For example, assuming that $\mathbf{T} = \mathbf{0}$ for rigid-body rotations, i.e., when $\mathbf{A} = \mathbf{R}$, then $\mathbf{T}^{(nc)} = \mathbf{0}$ when $\mathbf{F} = \mathbf{G}\mathbf{R}\mathbf{G}_0^{-1}$. In particular, in the absence of elastic deformations, such that $\mathbf{A} = \mathbf{I}$ and $\mathbf{G} = \mathbf{G}_0$, the undeformed configuration, with $\mathbf{F} = \mathbf{I}$, is stress free, i.e., $\mathbf{T}^{(nc)} = \mathbf{0}$. However, since it is possible for a stress-free state to be generated by more than one deformation, when these deformations are geometrically compatible, they can also alternate in the same material, producing an inhomogeneous pattern.

More generally, if $\mathbf{T} = p\mathbf{I}$, where p is constant, while $\mathbf{A} = c\mathbf{R}$, where c is constant and \mathbf{R} is a rigid-body rotation, then $\mathbf{T}^{(nc)} = p(\det \mathbf{G}^{-1} \det \mathbf{G}_0)\mathbf{I}$ for $\mathbf{F} = c\mathbf{G}\mathbf{R}\mathbf{G}_0^{-1}$. As it is possible for the same stress to be generated by different deformations, if these are geometrically compatible, then they can also alternate in the same material to produce inhomogeneous patterns.

Our result concerning controllable deformation in ideal nematic elastomers is established in the next section.

4 Controllable deformations

Theorem. For an ideal unconstrained uniaxial nematic LCE characterized by equation (1), such that \mathbf{G}_0 is constant in Cartesian coordinates, a deformation with gradient $\mathbf{F}(\mathbf{X})$ of differentiability class \mathcal{C}^2 , such that $\det \mathbf{F}(\mathbf{X}) > 0$, can be maintained for all $W^{(nc)}$ by the application of surface tractions only (without body forces) if and only if both \mathbf{F} and \mathbf{G} are constant in Cartesian coordinates.

Proof: We set the notation $\bar{\mathbf{F}} = \mathbf{F}\mathbf{G}_0$, so that $\bar{\mathbf{F}} = \mathbf{G}\mathbf{A}$ (see Figure 1). Since \mathbf{G}_0 is constant, this amounts to a change of coordinates from the cross-linking state, with coordinates (X_1, X_2, X_3) , to a virtual isotropic state, with coordinates $(\bar{X}_1, \bar{X}_2, \bar{X}_3)$, such that

$$G_{0ij} = \frac{\partial X_i}{\partial \bar{X}_j}, \quad i, j = 1, 2, 3. \quad (34)$$

Henceforth, all calculations are carried out within this new system of coordinates.




Figure 1: Schematic of multiplicative decomposition $\mathbf{F} = \mathbf{G}\mathbf{A}\mathbf{G}_0^{-1}$ and adopted notation $\mathbf{F}\mathbf{G}_0 = \bar{\mathbf{F}} = \mathbf{G}\mathbf{A}$.

The first Piola-Kirchhoff stress takes the form

$$\bar{\mathbf{P}}^{(nc)} = \frac{\partial W^{(nc)}}{\partial \bar{\mathbf{F}}} = \sum_{i=1}^5 \frac{\partial W^{(nc)}}{\partial I_i^{(nc)}} \frac{\partial I_i^{(nc)}}{\partial \bar{\mathbf{F}}}. \quad (35)$$

In the absence of body forces, the equation of elastostatic equilibrium is

$$\text{Div } \bar{\mathbf{F}}^{(nc)} = \mathbf{0}. \quad (36)$$

Equivalently,

$$\sum_{i=1}^5 \frac{\partial W^{(nc)}}{\partial I_i^{(nc)}} \text{Div} \left(\frac{\partial I_i^{(nc)}}{\partial \bar{\mathbf{F}}} \right) + \sum_{i=1}^9 \sum_{j=1}^3 \frac{\partial^2 W^{(nc)}}{\partial I_i^{(nc)} \partial I_j^{(nc)}} \left(\text{Grad } I_j^{(nc)} \right) \frac{\partial I_i^{(nc)}}{\partial \bar{\mathbf{F}}} = \mathbf{0}. \quad (37)$$

By the standard argument, if this holds for arbitrary $W^{(nc)}$, then

$$\text{Div} \left(\frac{\partial I_i^{(nc)}}{\partial \bar{\mathbf{F}}} \right) = \mathbf{0}, \quad i = 1, \dots, 5,$$

and

$$\left(\text{Grad } I_j^{(nc)} \right) \frac{\partial I_i^{(nc)}}{\partial \bar{\mathbf{F}}} + \left(\text{Grad } I_i^{(nc)} \right) \frac{\partial I_j^{(nc)}}{\partial \bar{\mathbf{F}}} = \mathbf{0}, \quad i, j = 1, \dots, 5.$$

In particular, if $i = j$, then

$$\text{Grad } I_i^{(nc)} = 0, \quad i = 1, \dots, 5.$$

For $i = 1$, $\partial I_1^{(nc)} / \partial \bar{\mathbf{F}} = 2\bar{\mathbf{F}}$, hence

$$\text{Grad } I_1^{(nc)} = \mathbf{0} \quad \text{and} \quad \text{Div} \left(\frac{\partial I_1^{(nc)}}{\partial \bar{\mathbf{F}}} \right) = 2 \text{Div } \bar{\mathbf{F}} = \mathbf{0}. \quad (38)$$

If the components of the deformation gradient are expressed in Cartesian coordinates as

$$\bar{F}_{ij} = \frac{\partial x_i}{\partial X_j}, \quad i, j = 1, 2, 3,$$

then $\text{Div } \bar{\mathbf{F}} = \mathbf{0}$ takes the form

$$\sum_{k=1}^3 \frac{\partial^2 x_i}{\partial \bar{X}_k^2} = 0, \quad i = 1, 2, 3,$$

and $\text{Grad } I_1^{(nc)} = \mathbf{0}$ can be written as

$$\sum_{i=1}^3 \sum_{j=1}^3 \frac{\partial x_i}{\partial X_j} \frac{\partial^2 x_i}{\partial X_j \partial X_k} = 0, \quad k = 1, 2, 3.$$

Therefore,

$$0 = \sum_{k=1}^3 \frac{\partial}{\partial \bar{X}_k} \left(\sum_{i=1}^3 \sum_{j=1}^3 \frac{\partial x_i}{\partial X_j} \frac{\partial^2 x_i}{\partial X_j \partial X_k} \right) = \sum_{i=1}^3 \sum_{j=1}^3 \sum_{k=1}^3 \frac{\partial^2 x_i}{\partial \bar{X}_j \partial \bar{X}_k} \frac{\partial^2 x_i}{\partial \bar{X}_j \partial \bar{X}_k}.$$

Noting that the right-hand side of the above equality is a sum of squares, it follows that

$$\frac{\partial^2 x_i}{\partial \bar{X}_j \partial \bar{X}_k} = 0, \quad i, j, k = 1, 2, 3.$$

Hence $\bar{\mathbf{F}}$ is constant in the Cartesian coordinates $(\bar{X}_1, \bar{X}_2, \bar{X}_3)$, and since \mathbf{G}_0 is constant, \mathbf{F} is also constant in the Cartesian coordinates (X_1, X_2, X_3) .

Next, we show that \mathbf{G} is constant as well. For $i = 4$,

$$\text{Grad } I_4^{(nc)} = \mathbf{0} \quad \text{and} \quad \text{Div} \left(\frac{\partial I_4^{(nc)}}{\partial \bar{\mathbf{F}}} \right) = \mathbf{0}. \quad (39)$$

Taking any finite deformation with $\bar{\mathbf{F}}$ constant, we choose the Cartesian coordinates along its principal directions, such that $\bar{\mathbf{F}} = \text{diag}(\bar{F}_{11}, \bar{F}_{22}, \bar{F}_{33})$. Then the first equation in $I_4^{(nc)}$ implies:

$$\begin{aligned}\bar{F}_{11} \frac{\partial n_1^2}{\partial \bar{X}_1} + \bar{F}_{22} \frac{\partial n_2^2}{\partial \bar{X}_1} + \bar{F}_{33} \frac{\partial n_3^2}{\partial \bar{X}_1} &= 0, \\ \bar{F}_{11} \frac{\partial n_1^2}{\partial \bar{X}_2} + \bar{F}_{22} \frac{\partial n_2^2}{\partial \bar{X}_2} + \bar{F}_{33} \frac{\partial n_3^2}{\partial \bar{X}_2} &= 0, \\ \bar{F}_{11} \frac{\partial n_1^2}{\partial \bar{X}_3} + \bar{F}_{22} \frac{\partial n_2^2}{\partial \bar{X}_3} + \bar{F}_{33} \frac{\partial n_3^2}{\partial \bar{X}_3} &= 0,\end{aligned}$$

while the second equation implies

$$\frac{\partial n_1^2}{\partial \bar{X}_1} = 0, \quad \frac{\partial n_2^2}{\partial \bar{X}_2} = 0, \quad \frac{\partial n_3^2}{\partial \bar{X}_3} = 0.$$

From the above equations, we infer that n_i is independent of \bar{X}_i , for $i = 1, 2, 3$, and the following conditions are satisfied simultaneously:

$$\begin{aligned}(\bar{F}_{11} - \bar{F}_{33}) \frac{\partial n_1^2}{\partial \bar{X}_2} &= 0, & (\bar{F}_{11} - \bar{F}_{22}) \frac{\partial n_1^2}{\partial \bar{X}_3} &= 0, \\ (\bar{F}_{22} - \bar{F}_{33}) \frac{\partial n_2^2}{\partial \bar{X}_1} &= 0, & (\bar{F}_{22} - \bar{F}_{11}) \frac{\partial n_2^2}{\partial \bar{X}_3} &= 0, \\ (\bar{F}_{33} - \bar{F}_{22}) \frac{\partial n_3^2}{\partial \bar{X}_1} &= 0, & (\bar{F}_{33} - \bar{F}_{11}) \frac{\partial n_3^2}{\partial \bar{X}_2} &= 0.\end{aligned}$$

By the isotropy condition (C2), we can apply any rotation \mathbf{R} prior to the deformation, such that $\{\bar{F}_{11}, \bar{F}_{22}, \bar{F}_{33}\}$ permute along the diagonal, while \mathbf{n} does not rotate. After replacing $\text{diag}(\bar{F}_{11}, \bar{F}_{22}, \bar{F}_{33})$ first with $\text{diag}(\bar{F}_{22}, \bar{F}_{33}, \bar{F}_{11})$ and second with $\text{diag}(\bar{F}_{33}, \bar{F}_{11}, \bar{F}_{22})$, we also obtain, respectively:

$$\begin{aligned}(\bar{F}_{22} - \bar{F}_{11}) \frac{\partial n_1^2}{\partial \bar{X}_2} &= 0, & (\bar{F}_{22} - \bar{F}_{33}) \frac{\partial n_1^2}{\partial \bar{X}_3} &= 0, \\ (\bar{F}_{33} - \bar{F}_{11}) \frac{\partial n_2^2}{\partial \bar{X}_1} &= 0, & (\bar{F}_{33} - \bar{F}_{22}) \frac{\partial n_2^2}{\partial \bar{X}_3} &= 0, \\ (\bar{F}_{11} - \bar{F}_{33}) \frac{\partial n_3^2}{\partial \bar{X}_1} &= 0, & (\bar{F}_{11} - \bar{F}_{22}) \frac{\partial n_3^2}{\partial \bar{X}_2} &= 0,\end{aligned}$$

and

$$\begin{aligned}(\bar{F}_{33} - \bar{F}_{22}) \frac{\partial n_1^2}{\partial \bar{X}_2} &= 0, & (\bar{F}_{33} - \bar{F}_{11}) \frac{\partial n_1^2}{\partial \bar{X}_3} &= 0, \\ (\bar{F}_{11} - \bar{F}_{22}) \frac{\partial n_2^2}{\partial \bar{X}_1} &= 0, & (\bar{F}_{11} - \bar{F}_{33}) \frac{\partial n_2^2}{\partial \bar{X}_3} &= 0, \\ (\bar{F}_{22} - \bar{F}_{11}) \frac{\partial n_3^2}{\partial \bar{X}_1} &= 0, & (\bar{F}_{22} - \bar{F}_{33}) \frac{\partial n_3^2}{\partial \bar{X}_2} &= 0.\end{aligned}$$

We distinguish the following two cases. First, if at least two of the three diagonal values $\{\bar{F}_{11}, \bar{F}_{22}, \bar{F}_{33}\}$ are different from each other, then $\text{Grad } \mathbf{n} = \mathbf{0}$, i.e., \mathbf{n} is uniform in the Cartesian coordinates $(\bar{X}_1, \bar{X}_2, \bar{X}_3)$, and since \mathbf{G}_0 is constant, \mathbf{n} is also uniform in the Cartesian coordinates (X_1, X_2, X_3) (see also [34]). Thus \mathbf{G} is constant. Second, if $\bar{F}_{11} = \bar{F}_{22} = \bar{F}_{33} = \bar{F}$, then $\bar{\mathbf{F}} = \bar{F}\mathbf{I}$, where \bar{F} is a constant scalar in the Cartesian coordinates $(\bar{X}_1, \bar{X}_2, \bar{X}_3)$. Hence, the current configuration is an isotropic state, i.e., \mathbf{G} is constant, in the Cartesian coordinates $(\bar{X}_1, \bar{X}_2, \bar{X}_3)$. Because \mathbf{G}_0 is constant, it follows that \mathbf{G} is constant also in the Cartesian coordinates (X_1, X_2, X_3) , i.e., either $\mathbf{n} = \mathbf{n}_0$ or both the reference and current configurations are isotropic.

Conversely, when \mathbf{F} and \mathbf{G} are constant in the Cartesian coordinates, given that \mathbf{G}_0 is constant, the equation of elastostatic equilibrium in the absence of body forces is automatically satisfied. This completes the proof.

We note that, when equal and opposite homogeneous shear deformations generate alternating shear stripes in LCEs as in soft (or semi-soft) elastic phenomena, the deformation gradient in two adjacent stripes are geometrically compatible (see, e.g., [22, Chapter 6]). Therefore, by assuming that the deformation gradient is piecewise of differentiability class \mathcal{C}^2 , the above theorem can be extended to shear-stripping patterns, which can also be maintained universally by the application of surface tractions only in ideal nematic elastomers. This is formally presented in the next result.

Corollary. For an ideal unconstrained uniaxial nematic LCE characterized by equation (1), such that \mathbf{G}_0 is constant in Cartesian coordinates, a deformation with gradient $\mathbf{F}(\mathbf{X})$ which is piecewise of differentiability class \mathcal{C}^2 , such that $\det \mathbf{F}(\mathbf{X}) > 0$, can be maintained for all $W^{(nc)}$ by the application of surface tractions only (without body forces) if and only if both \mathbf{F} and \mathbf{G} are piecewise constant in Cartesian coordinates. In two adjacent subdomains, the deformation gradient, \mathbf{F}_+ and \mathbf{F}_- , must be rank-one connected, i.e., $\text{rank}(\mathbf{F}_+ - \mathbf{F}_-) = 1$, for geometric compatibility.

5 Conclusion

For unconstrained uniaxial nematic LCEs described by a homogeneous isotropic strain-energy density function, we proved that the only deformations that are independent of the material parameters and can be maintained by the application of traction forces on the boundary of the body, assuming that the deformation gradient is sufficiently smooth, are the homogeneous deformations, i.e., those for which the deformation gradient is constant and the director is either uniform or randomly oriented in the Cartesian coordinates. This result is consistent with the classical Ericksen's theorem for nonlinear homogeneous isotropic hyperelastic materials, which is directly applicable to ideal LCEs in an isotropic phase. However, in a nematic phase, the constitutive strain-energy density is a function of five invariants instead of three, to account also for the liquid crystal orientation.

Since LCEs are to a large extent incompressible materials, and we know from the elastic case that this extra constraint guarantees the existence of additional universal solutions, there are also important inhomogeneous deformations that can be controlled by the application of surface tractions and are independent of the constitutive parameters. We refer to [1, 20, 24] where such deformations have been examined.

Acknowledgement: The authors would like to thank the Isaac Newton Institute for Mathematical Sciences for support and hospitality during the programme Uncertainty Quantification and Stochastic Modelling of Materials when work on this paper was undertaken. This work was supported by EPSRC Grant Number EP/R014604/1.

Conflict of interest: The authors have no conflict of interest.

Data availability statement: This paper has no data.

References

- [1] Carlson DE, Fried E, Sellers S. 2002. Force-free states, relative strain, and soft elasticity in nematic elastomers, *Journal of Elasticity* 69, 161-180 (doi: 10.1023/A:1027377904576).
- [2] Conti S, DeSimone A, Dolzmann G. 2002. Soft elastic response of stretched sheets of nematic elastomers: a numerical study, *Journal of the Mechanics and Physics of Solids* 50, 1431-1451 (doi: 10.1016/S0022-5096(01)00120-X).

- [3] de Gennes PG, Prost J. 1993. *The Physics of Liquid Crystals*, 2nd ed, Clarendon Press, Oxford.
- [4] de Jeu WH (ed). 2012. *Liquid Crystal Elastomers: Materials and Applications*, Springer, New York.
- [5] DeSimone A, Dolzmann G. 2000. Material instabilities in nematic elastomers, *Physica D. Nonlinear Phenomena* 136(1-2), 175-191 (doi: S0167-2789(99)00153-0).
- [6] DeSimone A, Teresi L. 2009. Elastic energies for nematic elastomers, *The European Physical Journal E* 29, 191-204 (doi: 10.1140/epje/i2009-10467-9).
- [7] Ericksen JL. 1954. Deformations possible in every isotropic, incompressible, perfectly elastic body, *Zeitschrift für angewandte Mathematik und Physik (ZAMP)* 5, 466-489.
- [8] Ericksen JL. 1955. Deformation possible in every compressible isotropic perfectly elastic materials, *Journal of Mathematics and Physics* 34, 126-128.
- [9] Finkelmann H, Greve A, Warner M. 2001. The elastic anisotropy of nematic elastomers, *The European Physical Journal E* 5, 281-293 (doi: 10.1007/s101890170060).
- [10] Finkelmann H, Kundler I, Terentjev EM, Warner M. 1997. Critical stripe-domain instability of nematic elastomers, *Journal de Physique II* 7, 1059-1069 (doi: 10.1051/jp2:1997171).
- [11] Fried E, Sellers S. 2004. Free-energy density functions for nematic elastomers, *Journal of the Mechanics and Physics of Solids* 52(7), 1671-1689 (doi: 10.1016/j.jmps.2003.12.005).
- [12] Fried E, Sellers S. 2005. Orientational order and finite strain in nematic elastomers, *The Journal of Chemical Physics* 123(4), 043521 (doi: 10.1063/1.1979479).
- [13] Fried E, Sellers S. 2006. Soft elasticity is not necessary for striping in nematic elastomers, *Journal of Applied Physics* 100, 043521 (doi: 10.1063/1.2234824).
- [14] Goodbrake C, Yavari A, Goriely A. 2020. The anelastic Ericksen problem: Universal deformations and universal eigenstrains in incompressible nonlinear anelasticity, *Journal of Elasticity* 142(2), 291-381 (doi: 10.1016/j.jmps.2019.103782).
- [15] Golubović L, Lubensky TC. 1989. Nonlinear elasticity of amorphous solids, *Physical Review Letters* 63, 1082-1085 (doi: 10.1103/PhysRevLett.63.1082).
- [16] Higaki H, Takigawa T, Urayama K. 2013. Nonuniform and uniform deformations of stretched nematic elastomers, *Macromolecules* 46, 5223-5231 (doi: 10.1021/ma400771z).
- [17] Klingbeil WW, Shield RT. 1966. On a class of solutions in plane finite elasticity, *Journal of Applied Mathematics and Physics (ZAMP)* 17, 489-511 (doi: 10.1007/BF01595984).
- [18] Kundler I, Finkelmann H. 1995. Strain-induced director reorientation in nematic liquid single crystal elastomers, *Macromolecular Rapid Communications* 16, 679-686 (doi: 10.1002/marc.1995.030160908).
- [19] Kundler I, Finkelmann H. 1998. Director reorientation via stripe-domains in nematic elastomers: influence of cross-link density, anisotropy of the network and smectic clusters, *Macromolecular Chemistry and Physics* 199, 677-686.
- [20] Lee V, Bhattacharya K. 2023. Universal deformations of incompressible nonlinear elasticity as applied to ideal liquid crystal elastomers, *Journal of Elasticity* (doi: 10.1007/s10659-023-10018-9).
- [21] Marris AW, Shiau JF. 1970. Universal deformations in isotropic incompressible hyperelastic materials when the deformation tensor has equal proper values, *Archive for Rational Mechanics and Analysis* 36, 135-160 (doi: 10.1007/BF00250814).

- [22] Mihai LA. 2022. Stochastic Elasticity: A Nondeterministic Approach to the Nonlinear Field Theory, Springer Cham, Switzerland (doi: <https://doi.org/10.1007/978-3-031-06692-4>).
- [23] Mihai LA, Goriely A. 2020. Likely striping in stochastic nematic elastomers, *Mathematics and Mechanics of Solids* 25(10), 1851-1872 (doi: [0.1177/1081286520914958](https://doi.org/10.1177/1081286520914958)).
- [24] Mihai LA, Goriely A. 2021. Instabilities in liquid crystal elastomers, *Material Research Society (MRS) Bulletin* 46 (doi: [10.1557/s43577-021-00115-2](https://doi.org/10.1557/s43577-021-00115-2)).
- [25] Mihai LA, Mistry D, Raistrick T, Gleeson HF, Goriely A. 2022. A mathematical model for the auxetic response of liquid crystal elastomers, *Philosophical Transaction of the Royal Society A* 380, 20210326 (doi: [10.1098/rsta.2021.0326](https://doi.org/10.1098/rsta.2021.0326)).
- [26] Petelin A, Čopič M. 2009. Observation of a soft mode of elastic instability in liquid crystal elastomers, *Physical Review Letters* 103, 077801 (doi: [10.1103/PhysRevLett.103.077801](https://doi.org/10.1103/PhysRevLett.103.077801)).
- [27] Petelin A, Čopič M. 2010. Strain dependence of the nematic fluctuation relaxation in liquid-crystal elastomers, *Physical Review E* 82, 011703 (doi: [10.1103/PhysRevE.82.011703](https://doi.org/10.1103/PhysRevE.82.011703)).
- [28] Saccomandi G. 2001. Universal solutions and relations in finite elasticity, in *Topics in Finite Elasticity*, M. Hayes and G. Saccomandi, eds., Springer-Verlag, Wien, 95–130.
- [29] Shield RT. 1971. Deformations possible in every compressible, isotropic, perfectly elastic material, *Journal of Elasticity* 1, 91-92.
- [30] Spencer AJM. 1971. Theory of invariants. In: Eringen, A.C. (ed.) *Continuum Physics* 1, 239-253, Academic Press, New York.
- [31] Talroze RV, Zubarev ER, Kuptsov SA, Merekalov AS, Yuranova TI, Plate NA, Finkelmann H. 1999. Liquid crystal acrylate-based networks: polymer backbone-LC order interaction, *Reactive and Functional Polymers* 41, 1-11 (doi: [10.1016/S1381-5148\(99\)00032-2](https://doi.org/10.1016/S1381-5148(99)00032-2)).
- [32] Warner M, Terentjev EM. 2007. *Liquid Crystal Elastomers*, paper back, Oxford University Press, Oxford, UK.
- [33] Yavari A, Goriely A. 2016. The anelastic Ericksen problem: Universal eigenstrains and deformations in compressible isotropic elastic solids, *Proceedings of the Royal Society A* 472(2196), 20160690 (doi: [10.1098/rspa.2016.0690](https://doi.org/10.1098/rspa.2016.0690)).
- [34] Yavari A, Goriely A. 2021. Universal deformations in anisotropic nonlinear elastic solids, *Journal of the Mechanics and Physics of Solids* 156, 104598 (doi: [10.1016/j.jmps.2021.104598](https://doi.org/10.1016/j.jmps.2021.104598)).
- [35] Yavari A, Goriely A. 2022. The universal program of nonlinear hyperelasticity, *Journal of Elasticity*, 1–56 (doi: [10.1007/s10659-022-09906-3](https://doi.org/10.1007/s10659-022-09906-3)).
- [36] Zubarev ER, Kuptsov SA, Yuranova TI, Talroze RV, Finkelmann H. 1999. Monodomain liquid crystalline networks: reorientation mechanism from uniform to stripe domains, *Liquid Crystals* 26, 1531-1540 (doi: [10.1080/026782999203869](https://doi.org/10.1080/026782999203869)).